

### SPECIFICATIONS

Commercial	5454
EN	5454

Aluminium alloy 5454 has very good corrosion resistance, in particular to seawater and general environmental conditions. Strength is medium to high and similar alloy 5754 with good strength in the temperature range 65 to 170 degrees centigrade. It has a high fatigue strength. It is not suitable for complex or fine extrusions.

Applications 5454 is typically used in:

- ~ Road Transport Body-Building
- ~ Cemical and Process Plant
- ~ Pressure Vessels, Containers, Boilers
- ~ Cryogenics
- ~ Marine & Off-shore incl. Masts,
- ~ Pylons, poles & masts

### CHEMICAL COMPOSITION

BS EN 573-3:2009 Alloy 5454	
Element	% Present
Magnesium (Mg)	2.4 - 3
Manganese (Mn)	0.5 - 1
Iron (Fe)	0.4 max
Silicon (Si)	0.25 max
Zinc (Zn)	0.25 max
Chromium (Cr)	0.05 - 0.2
Titanium (Ti)	0.2 max
Others (Total)	0.15 max
Copper (Cu)	0.1 max
Other (Each)	0.05 max
Aluminium (Al)	Balance

### ALLOY DESIGNATIONS

Alloy 5454 corresponds to the following standard designations and specifications **but may not be a direct equivalent:**

A5454

ISO Al Mg3MN

Al 2.7Mg 0.8Mn Cr

### TEMPER TYPES

The most common tempers for 5454 aluminium are shown below

- O - Soft
- H111 - Some work hardening imparted by shaping processes but less than required for H11 temper
- H22 - Work hardened by rolling then annealed to quarter hard
- H32 - Work hardened by rolling then stabilised by low-temperature heat treatment to quarter hard

### SUPPLIED FORMS

Alloy 5454 is supplied in most forms but is not suitable for fine or complex extrusions:

- Plate
- Sheet
- Bar
- Treadplate/Patterned Sheet
- Tube
- Wire

### GENERIC PHYSICAL PROPERTIES

Property	Value
Density	2.69 g/cm <sup>3</sup>
Melting Point	645 °C
Thermal Expansion	23.6 x10 <sup>-6</sup> /K
Modulus of Elasticity	70.5 GPa
Thermal Conductivity	135 W/m.K
Electrical Resistivity	34 % IACS

### MECHANICAL PROPERTIES

BS EN 485-2:2008 Sheet 0.2mm to 6.0mm	
Property	Value
Proof Stress	85 Min MPa
Tensile Strength	215 - 275 MPa
Hardness Brinell	58 HB

*Properties above are the range for material in the 'O'/H111 conditions*

### WELDABILITY

Alloy 5454 has good weldability by some methods but Soldering and Brazing are not recommended.

## FABRICATION

Formability of Alloy 5454 is good in the softer tempers and it can be extruded.

## CONTACT

Address:	Aldridge Warehouse No. 1 Wharf Approach Anchor Brook Industrial Park Aldridge Walsall WS9 8BX
Tel:	+44 (0)19 2245 3982
Email:	sales@durbinmetals.co.uk
Web:	www.durbinmetals.co.uk

## REVISION HISTORY

Datasheet Updated	13 November 2018
-------------------	------------------

## DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.